



ECOPAPER COPY

MAXIMUM PERFORMANCE

SPECIFICATION	DOC. NO.	SP/6/91/1675
	REVISION	12
	DATE OF ISSUE	21/09/20
	PAGE	1 OF 1
TITLE: PHOTOCOPY PAPER TRUTONE BLUISH WHITE 70, 75, 80 GSM		

NO.	PARAMATER	UNIT	VALUE			TEST METHOD
			70 GSM	75 GSM	80 GSM	
1.	Basis Weight	g/m ²	70 ± 4%	75 ± 4%	80 ± 4%	ISO 536:2019
2.	Thickness	µm	94 ± 4	99 ± 4	106 ± 4	ISO 534:2011
3.	Bendtsen Roughness	ml/min	Max. 275	Max. 275	Max. 275	ISO 8791-2:2013
4.	ISO Brightness	%	95 ± 1	95 ± 1	95 ± 1	ISO 2470-1:2016
5.	ISO Opacity	%	Min. 89	Min. 90	Min. 91	ISO 2471:2008
6.	CIE Whiteness (D65/10°)	%	160 ± 4	160 ± 4	160 ± 4	ISO 11475:2017
7.	Cobb / 60 Seconds	g/m ²	25 ± 5	25 ± 5	25 ± 5	TAPPI T441 om-13

Prepared by		Approved by	
Sec. Head (Laboratory) Date: 21/09/2020	Dept. Head (Laboratory) Date: 21/09/2020	Production Manager Date: 21/09/2020	Head of Quality Division Date: 21/09/2020

