



APP INDUSTRIAL PAPERBOARD BUSINESS UNIT
GUANGXI JINGUI PULP&PAPER CO., LTD



ALLYKING CREAM

Technical Information	Unit	Margin	Specification							Standards
Basis Weight	g/m ²	±3%	215	235	250	270	295	325	350	ISO536
Caliper	pt	±3%	13.8	15.1	16.5	18.1	20.0	22.0	24.0	
Thickness	μm	±3%	350	385	420	460	510	560	610	ISO 534
Stiffness (15°)CD	mN • m	±10%	5.32	7.05	8.31	10.8	15.2	17.8	24.5	ISO 2493
Stiffness (15°)MD	mN • m	±10%	9.48	12.6	15.8	20.9	29.3	32.2	40.0	
Moisture	%	±1.0	7.0							ISO287
Roughness-top	μm	≤	1.7							ISO 8791-4
Brightness D65/10 -top	%	±2.0	82.0							ISO 2470-1
Gloss-top	%	±5	40							TAPPI480
IGT-top	m/s	≥	1.20							ISO 8254-1
Cobb 60s-top	g/m ²	≤	55							ISO 535
Scott Plybonding	J/m ²	≥	130							TAPPI 569
Squareness	mm	≤	2.0							GB/T 451.1
Size Deviation	mm	≤	2.0							
Hygienic Standard	Qualified by <<Hygienic Standard of paper used for food packaging>>									GB11680-1989

Test climate 23°C/50%RH (according to ISO 187)