



金东纸业(江苏)股份有限公司

GOLD EAST PAPER (JIANGSU) CO.,LTD.

中国江苏省镇江市大港兴港东路8号 邮编212132

8, Xingang Dong Rd., Dagang, Zhenjiang 212132, Jiangsu. PR China

Telephone : +86- 511- 88998888 Fax : +86- 511- 88997000 Web:www.goldeastpaper.com.cn

Specifications

EASY SILK

Jul. 2018 H Edition

Item	Unit	Test Method Reference	90 g/m ²	100 g/m ²	110 g/m ²	115 g/m ²	125 g/m ²	130 g/m ²	145 g/m ²	150 g/m ²	170 g/m ²
Basis Weight	g/m ²	ISO 536	90	100	110	115	125	130	145	150	170
Thickness	μm	T 411	78	87	96	102	111	117	132	141	156
Brightness	%	ISO 2470/1	81	81	81	81	81	81	81	81	81
Opacity	%	ISO 2471	95	96	96	97	97	98	98	98	98
Roughness	μm	ISO 8791/4	1.8	1.8	1.8	1.8	2.0	2.0	2.2	2.2	2.3
Gloss	%	T 480	32	32	32	32	32	32	32	32	32

Remark: Above are average value.

GOLD EAST PAPER (JIANGSU) CO.,LTD.

