

UPM Office presentation

Choose UPM Office cut-size papers when you need to be absolutely sure to produce optimal printing quality. Suitable for anything from superior-quality colour printouts to functional high speed copying.

Recommended end-uses

Colour diagrams | Correspondence | Direct mailing | Documents | Flyers | High-quality documents | Leaflets | Manuals | Memos | Newsletters | Office applications | Office paper | Product data sheets | Reports | Transactional / transpromotional documents

Product information

| Regions | South America Africa Europe Middle East | | |
|------------------|---|--|--|
| Business contact | UPM Communication Papers | | |
| Category | Office papers | | |
| Description | High quality office paper for excellent print results with high contrasts and vivid colours. | | |
| Grade | Woodfree uncoated (WFU) | | |
| Finish | Machine finished | | |
| Furnish | Chemical pulp | | |
| Printing method | B/W inkjet printing B/W laser printing (dry toner) Colour inkjet printing Colour laser printing (dry toner) Copying | | |
| Format/Size | A5 A4 A3 | | |
| Wrapping | UPM Asendo™ | | |
| Note | FSC® certified. | | |
| | | | |

Certificates

| Product Compliance | EU Ecolabel Permanent Paper ISO 9706 |
|-----------------------|---|
| Fibre Certificates | FSC Chain-of-Custody |
| Mill Certificates | ISO 50001 ISO 9001 ISO 14001 ISO 45001 EMAS |
| Other Certificates | HP ColorLok |

Technical target values

| Basis weight (ISO 536) (g/m²) | 80.0 | 90.0 * | 100.0 * |
|--|-------|--------|---------|
| Thickness (ISO 534) (µm) | 105.0 | 118.0 | 131.0 |
| CIE Whiteness (ISO 11475) | 170.0 | 170.0 | 170.0 |
| Brightness D65 (ISO 2470-2) (%) | 110.0 | 110.0 | 110.0 |
| Opacity ISO (2471) (%) | 95.0 | 96.0 | 97.0 |
| Roughness Bendtsen (ISO 8791-2) (ml/min) | 150.0 | 180.0 | 180.0 |

^{* 90} and 100 g/m² available on request.

Please note: Technical values are informative and subject to production variations.